

sikkens



application by brush



application via spatula



for windows



for doors



limited dimension stable wooden constructions



store and transport in a frost free area



store in a cool place



cleaning of equipment with water

Kodrin WV 456

Product description	Sealing matter in a water base for closing endgrain porous areas, exterior and interior.
Properties	- a neutral odour - quick drying - easy to apply
Colour	Colorless
Binder type	Special polymer dispersion
Density (specific weight)	approx. 1,00 - 1,03 kg/l
Packaging	750 ml
Processing	Brush, spatula
Consumption	Approx. 100 ml/m ²
Thinning	Do not thin down
Application temperature	15-25 °C for substrate, air and material at 60 % R.H.
Drying times	Drying at 23 °C/50 % R.H. DIN 50014 Dust dry: after approx. 30 Minutes Recoatable: earliest after approx 1 hour waterborne The drying process of the material can be delayed depending of thickness and when using timber with a high extract contents in damp/cold weathering conditions. During the drying process one should ensure for adequate airing and temperature conditions.
Cleaning of equipment	Clean directly after use with water or washing up liquid or with ST 830* (cleaning agent).
Storage	Minimum storage stability: 1 year Opened cans must be properly closed! Store in a cool but frost-protected area.
Disposal	Only residue emptied cans can be disposed via recycling (Interseroh, DSD). Liquid wastes must be disposed of according to national regulations or according to EU-disposal key 08 01 12.
Hazard identification	Hazard symbol: - If swallowed, seek medical advice immediately and show this container or label. Safety data sheet available for professional user on request. Keep out of the reach of children.
Warning	Before use, read the identification and product information. Even when working with low emission products one should take care of the customary protection measures.
VOC guideline	Out of scope.
General instructions	The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %. According to the guidelines for window coating systems, published by the Federal German Committee for Paint and Material Value Protection (Instruction Leaflet No. 18), of VOB, Part C, DIN 18363, and the Recommendations of the German Institute for Window Technology e.V. in Rosenheim, all wooden constructions in buildings must be coated on all sides with at least one primer and one intermediate coat (minimum dry film thickness 30 µm) before they are incorporated in buildings. The choice and use of the coating system, especially the colour shade, should also be taken into account. Darker shades can increase the surface temperature (up to 80° C).

All details on our products contained in this publication do not represent details of the quality of the goods. The quality, suitability, qualification and function intended use of our goods shall be determined exclusively in accordance with the product descriptions based on the respective sales agreements. In each case, deviations typical of the sector shall be admissible, unless agreed in writing otherwise. All details correspond to today's state of technology. We make no claim as to the completeness of the stated coating installations; they are stated merely as possible examples. Due to the large number of substrates and object conditions, the buyer/user shall not be released from his/her obligation to check our raw materials in a workmanlike manner for their suitability for the intended purpose on his/her own responsibility subject to the respective property conditions and process these in accordance with the respective state of technology. In other respects, our standard terms and conditions of sale apply. Upon the appearance of a new edition, this publication shall lose its validity.

Akzo Nobel Industrial Coatings Ltd
Dulux Paints, Shandon Works
Akzo Nobel Wood Products
Akzo Nobel Deco GmbH

Unit 4a, Mercer Way, Shadsworth Bus Pk
Commons Road
220 rue St-Louis
Werner-von-Siemensstrasse 11

Blackburn, Lancs, BB12QZ
Cork
Warwick, Québec
31515 Wunstorf

United Kingdom
Rep of Ireland
Canada J0A 1M0
Germany

Tel. +44 1254 687950
Tel. +35 (0) 21 4220222
Tel. +49 (0) 5031 961-0

Fax. +44 1254 687960
Fax. +35 (0) 21 4220205
Fax. +49 (0) 5031 961-274