


Tip Wear



Spray pattern width	305mm New 515 Tip	280mm Worn to .017	229mm Worn to .019	140mm Worn to .021
Flow Rate	0.87 ltr/min	1.14 ltr/min	1.4 ltr/min	1.74 ltr/min
Flow Rate Increase		+30%	+61%	+100%

Depending on materials sprayed and care of equipment, a new tip is required after approximately 2 months of continuous spraying. As shown excessive wastage of materials will eventually outweigh cost of new tip.

